



Technical Data Sheet

[Z] ZowoTec® 340 Crosslinker

Product Description

Product Type

Water-based crosslinker to improve the insulation properties of [Z] ZowoTec® 340 InterCoat IsoX Spray

- » Improves the insulation properties of [Z] ZowoTec® 340 InterCoat IsoX Spray on larch wood
- » 4 hours potlife after incorporation into the basecoat
- » Easy to use
- » Other properties like processing, anti-sagging and drying time of the [Z] ZowoTec® 340 InterCoat IsoX Spray stay on the same level.

Area of Application

[Z] ZowoTec® 340 InterCoat IsoX Spray

Technical Data

Color	Colorless
Density	1,01 g/ml

Processing Instructions

Application Method

Work into [Z] ZowoTec® 340 InterCoat IsoX Spray with an addition of 10 weight- or volume parts [Z] ZowoTec® 340 Crosslinker, using a stirrer or shaker.

Processing Viscosity

Ready to use

Processing Conditions

- » To avoid flocculation, may not get in contact with solvents.
- » Maximum amount added: 10% by weight [Z] ZowoTec® 340 Crosslinker into the base coat [Z] ZowoTec® 340 InterCoat IsoX Spray
- » Pot life at 20 °C approx. 4 hours.
- » The viscosity of the mixture of base coat and hardener increases after 4 hours.
- » Do not use the material after pot life has been exceeded.

Cleaning of the Tools

Immediately after use with water or [Z] ZowoSmart® HydroCleaner.

Type of packaging

1 Liter

Additional Information

Special Information

- » Perform a test coating. Check color before use. Subsequent claims cannot be considered. Wood ingredients can cause discoloration!
- » Use only one batch no. per layer and color tone!
- » Please observe Berger-Zobel steps of coating!

Minimum Shelf Life

6 months cool but free of frost in the closed original packaging.

Safety Instructions

Always read label and product information before use. Please observe the usual precautions during processing and storage. For safety-relevant data and instructions on disposal refer to the Material Safety Data Sheet.



Berger-Zobel GmbH · Coating Systems
Maybachstr. 2 · D-67269 Grünstadt

+ 49 63 59 / 80 05 - 500
+ 49 63 59 / 80 05 - 177

info@berger-zobel.de
www.berger-zobel.de

Technical Data Sheet